

## Classifications

EN 14700	DIN 8555
T Z Fe6	MF 6-GF-60-GP

## Characteristics

Martensitic Chromium-Titanium alloy designed to resist high stress abrasion with heavy impact. Deposits usually do not relieve cracks.

Microstructure: Finely dispersed Titanium carbides in a hard Chromium martensitic matrix

Machinability: Grinding only

Oxy-acetylene cutting: Cannot be flame cut

Deposit thickness: 15 to 18 mm in 5 to 6 layers

## Field of use

Crusher rollers, crusher hammers, asphalt mixer blades, agricultural tools, shovel bucket teeth and lips, bulldozer blades, cane knives and shredders, bed knives in the wood pulp industry.

## Typical analysis in %

C	Mn	Si	Cr	Mo	Ti	Fe
1.8	0.9	0.2	6.1	1.4	5.5	balance

## Typical mechanical properties

Hardness as welded: 58 HRC

## Recommended welding parameters

Wire diameter [mm]	Amperage [A]	Voltage [V]	Stick-Out [mm]
1.2	120 – 150	26 – 30	35 – 40
1.6	180 – 200	26 – 30	35 – 40
2.0	200 – 280	26 – 30	35 – 40
2.4	250 – 300	26 – 30	35 – 40
2.8	300 – 350	26 – 30	35 – 40